

**Report Number:** BOMT16019728





TEST REPORT

NUMBER : BOMT16019728
DATE : 10-May-2016

APPLICANT : SWAYAM NIRYAT

A/803, SAMPRAT - 2,NR. KIRAN MOTORS, OPP. RAJPATH CLUB, S.G. HIGHWAY, BODAKDEV,, AHMEDABAD, GUJARAT, 380015, INDIA

ATTN : SANJAY TIWARI

Sample Description : ONE PIECE OF SUBMITTED WOVEN FABRIC SAMPLE.

END USE: SHIRTING

BTI-CORD-2

Applicant Provided Care Instructions :











Date Received/Date Test Started: 06 May 2016

Date Confirmation Received : Buyer Name : SASO

Style No :

Order No : JTR/6812

Color :-

Fiber Content : 50% POLYESTER & 50% COTTON

Performance No.

Vendor Name : SWAYAM NIRYAT

Buyer Name : SASO

TEST CONDUCTED: AS PER THE REQUEST OF THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO ENCLOSED PAGE(S)

CONCLUSION:

FIBRE IDENTIFICATION/COMPOSITION \*
LABELLING \*
Colour Fastness to Washing F
pH Value M

NOTE: M = MEETS REQUIREMENT, F = FAILS TO MEET REQUIREMENT

\* = REQUIREMENT NOT PROVIDED, NA = NOT APPLICABLE # = SEE REMARK, C = CONFIRM LABEL

AUTHORIZED BY

FOR Intertek India Private Limited - [Mumbai]

SUNDARMURTHY KRISHNAN NATIONAL HEAD - PHYSICAL



TEST REPORT

NUMBER: BOMT16019728 DATE : 10-May-2016

TEST CONDUCTED (AS REQUESTED BY THE APPLICANT)

## 1. FIBRE IDENTIFICATION/COMPOSITION

SASO 781: 1994

Marked

WARP Polyester WEFT Cotton

FIBRE COMPOSITION (ON FABRIC BASIS) :

Cotton : 51.9% 50% Cotton Polyester: 48.1%

50% Polyester

Marked

REMARK:

ISO: Annex IX of REGULATION (EU) No 1007/2011 repealing Directive 73/44/EEC and Directives

96/73/EC and 2008/121/EC

Cotton: 8.5% Polyester : 1.5%

# 2. LABELLING

VISUAL

Requirement

Present

Present-Art Work FIBER CONTENT WASHCARE LABEL Present-Art Work ARABIC WORDS OF CARE LABELING Present-Art Work ALL 5 SYMBOLS OF CARE LABEL Present-Art Work COUNTRY OF ORIGIN Present-Art Work





TEST REPORT

NUMBER : BOMT16019728 DATE : 10-May-2016

## 3. Colour Fastness to Washing

SASO 2329

, 30 MIN MECHANICAL WASH AT  $40^{\circ}$ C, IN 0.4% ECE(B) REFERENCE DETERGENT SOLUTION AND 0.1% SODIUM PERBORATE WITH 10 STEEL BALLS.

			<u>Requirement</u>
COLOUR CHANGE		4	4 (Min.)
COLOUR STAINING	ACETATE	4	4 (Min.)
	COTTON	3-4	
	NYLON	4-5	
	POLYESTER	4-5	
	ACRYLIC	4-5	
	WOOL	4-5	

## 4. pH Value

SASO 2144

RESULT 7.8 Requirement

With skin- 4.0 to 7.5

## ## END OF THE TEST REPORT ##

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Addressee in respect of this report and only accepts liability to the Addressee insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute.