

Report Number : BOMT18059293



TEST REPORT

NUMBER : BOMT18059293
DATE : 12-Oct-2018

APPLICANT : SWAYAM NIRYAT
A/803, Samprat - 2, Nr. Kiran Motors, Opp.
Rajpath Club, S.g. Highway, bodakdev,,
Ahmedabad, Gujarat, 380015, India
ATTN : Sanjay Tiwari

Sample Description : ONE PIECE OF SUBMITTED WOVEN FABRIC SAMPLE.
END USE: UNIFORM DRESS/SHIRTING

Applicant Provided Care Instructions :



Date Received/Date Test Started : 01 Oct 2018
Date Confirmation Received : 12 Oct 2018
Buyer Name : SASO
Style No : UNIFORM /11186
Order No : -
Color : -
Fiber Content : 70% POLYESTER, 30% VISCOSE
Performance No. : SASO GSO 1829/2007
Season : SEPT-2018
Manufacturer's Name : SWAYAM NIRYAT
Vendor Name : Swayam Niryat
Buyer Name : SASO

TEST CONDUCTED : AS PER THE REQUEST OF THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO ENCLOSED PAGE(S)

AUTHORIZED BY
FOR Intertek India Private Limited - [Mumbai]

INDIRA DEVADIGA
LAB MANAGER

TEST REPORT

NUMBER : BOMT18059293
DATE : 12-Oct-2018

CONCLUSION :

Fibre Identification/composition	*
Colour Fastness to Washing	M
pH Value	M
Labelling	*

NOTE :

M = MEETS REQUIREMENT,	F = FAILS TO MEET REQUIREMENT
* = REQUIREMENT NOT PROVIDED,	NA = NOT APPLICABLE
# = SEE REMARK,	C = CONFIRM LABEL
- = NOT PERFORMED	
NR = NOT REQUESTED	

TEST REPORT

NUMBER : BOMT18059293

DATE : 12-Oct-2018

TEST CONDUCTED (AS REQUESTED BY THE APPLICANT)

1. Fibre Identification/composition

SASO 781: 1994

Warp	Polyester+Viscose	<u>Marked</u>
Weft	Polyester+Viscose	
FIBRE COMPOSITION (ON FABRIC BASIS) :	Polyester : 69.6%	<u>Marked</u>
	Viscose : 30.4%	70% Polyester
		30% Viscose

REMARK:

ISO: Annex IX of REGULATION (EU) No 1007/2011 repealing Directive 73/44/EEC and Directives 96/73/EC and 2008/121/EC

Polyester : 1.5%

Viscose : 13.0%

2. Colour Fastness to Washing

AATCC 61

(2A, MODIFIED 45 MIN MECHANICAL WASH AT 105°F, IN 0.15% AATCC WOB DETREAGENT SOLUTION WITH 50 STEEL BALLS.)

Colour Change	4.0	<u>Requirement</u>
COLOUR STAINING		4 (Min.)
Acetate	4.5	4 (Min.)
Cotton	4.5	
Nylon	4.5	
Polyester	4.5	
Acrylic	4.5	
Viscose	4.5	
Wool	4.5	

3. pH Value

SASO 2144

7.5	<u>Requirement</u>
	Direct contact
	with skin- 4.0
	to 7.5

TEST REPORT

NUMBER : BOMT18059293
DATE : 12-Oct-2018

4. Labelling

VISUAL

		<u>Requirement</u>
Fiber Content	Present - Artwork	Present - Artwork
Washcare Label	Present - Artwork	Artwork
Arabic Words of Care Labeling	Present - Artwork	
Size	Present - Artwork	
Country of Origin	Present - Artwork	

SASO STANDARDS		
MANUFACTURER / EXHIBITOR	SWAYAM NIVAT swayamnivat@gmail.com Tel: 8 6991 971266081	المصنع / المصنوع
BUYER	SASO	المشتري
PRODUCT NAME	UNIFORM / 1186	اسم المنتج
COMPOSITION / CONTENT	AFT: 70% POLYESTER 30% VISCOSE	التصميم / لوت رقم
DESIGN / COLOR NO.		التركيبة / المصنوع من
WEIGHT (GSM)	190GSM (+/- 3%)	الوزن (GSM)
WIDTH	148 CM / 58 INCHES	عرض
LENGTH	AFT: 23 YARDS / 21.30 METERS	الطول
PURPOSE OF USE	UNIFORM DRESS / SHIRTING	الغرض من الاستخدام
COUNTRY OF ORIGIN	INDIA	بلد المنشأ
DATE OF MANUFACTURE	SEPTEMBER 2018	تاريخ التصنيع
WASHING AND IRONING CARE INSTRUCTIONS		
تعليمات غسل الملابس		
WASH BELOW 40 DEGREE CELSIUS	WASH 40 درجة CELSIUS	لا تستخدم مياه
DO NOT BLEACH		لا تستخدم مبيض
TUMBLE DRY LOW		يجفف بالتدوير بدرجة الحرارة المنخفضة
IRON AT NORMAL TEMPERATURE		لا تستخدم للتجفيف الجاف
DO NOT DRY CLEAN		لا تغسل
DRY IN SHADE ONLY		يجفف في الظل فقط
		
MADE IN INDIA		
المصنوع في الهند		

END OF THE TEST REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Addressee in respect of this report and only accepts liability to the Addressee insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute.