


Report Number :

BOMT18059295

BOMT18059295




TEST REPORT

NUMBER : BOMT18059295
DATE : 12-Oct-2018

APPLICANT : SWAYAM NIRYAT
A/803, Samprat - 2, Nr. Kiran Motors, Opp.
Rajpath Club, S.g. Highway, bodakdev,,
Ahmedabad, Gujarat, 380015, India
ATTN : Sanjay Tiwari

Sample Description : ONE PIECE OF SUBMITTED WOVEN FABRIC SAMPLE.
END USE: UNIFORM DRESS/SHIRTING

Applicant Provided Care Instructions :



Date Received/Date Test Started : 01 Oct 2018
Date Confirmation Received : 12 Oct 2018
Buyer Name : SASO
Style No : OXFORD
Order No : -
Color : -
Fiber Content : 60% COTTON, 40% POLYESTER
Performance No. : SASO GSO 1829/2007
Season : SEPT-2018
Manufacturer's Name : SWAYAM NIRYAT
Vendor Name : Swayam Niryat
Buyer Name : SASO

TEST CONDUCTED : AS PER THE REQUEST OF THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO ENCLOSED PAGE(S)

AUTHORIZED BY
FOR Intertek India Private Limited - [Mumbai]

INDIRA DEVADIGA
LAB MANAGER

TEST REPORT

NUMBER : BOMT18059295
DATE : 12-Oct-2018

CONCLUSION :

Fibre Identification/composition	*
Colour Fastness to Washing	M
pH Value	M
Labelling	*

NOTE:

M = MEETS REQUIREMENT,	F = FAILS TO MEET REQUIREMENT
* = REQUIREMENT NOT PROVIDED,	NA = NOT APPLICABLE
# = SEE REMARK,	C = CONFIRM LABEL
- = NOT PERFORMED	
NR = NOT REQUESTED	

TEST REPORT

NUMBER : BOMT18059295
DATE : 12-Oct-2018

TEST CONDUCTED (AS REQUESTED BY THE APPLICANT)

1. Fibre Identification/composition

SASO 781: 1994

Warp	Polyester	<u>Marked</u>
Weft	Cotton	
FIBRE COMPOSITION (ON FABRIC BASIS) :	Cotton : 61.3%	<u>Marked</u>
	Polyester : 38.7%	60% Cotton
		40% Polyester

REMARK:

ISO: Annex IX of REGULATION (EU) No 1007/2011 repealing Directive 73/44/EEC and Directives 96/73/EC and 2008/121/EC

Cotton : 8.5%
Polyester : 1.5%

2. Colour Fastness to Washing

AATCC 61
(2A, MODIFIED 45 MIN MECHANICAL WASH AT 105°F, IN 0.15% AATCC WOB DETREAGENT SOLUTION WITH 50 STEEL BALLS.)

Colour Change	4.0	<u>Requirement</u>
COLOUR STAINING		4 (Min.)
Acetate	4.5	4 (Min.)
Cotton	4.5	
Nylon	4.5	
Polyester	4.5	
Acrylic	4.5	
Wool	4.5	

3. pH Value

SASO 2144

7.4	<u>Requirement</u>
	Direct contact with skin- 4.0 to 7.5

TEST REPORT

NUMBER : BOMT18059295
DATE : 12-Oct-2018

4. Labelling

VISUAL

		<u>Requirement</u>
Fiber Content	Present - Artwork	Present - Artwork
Washcare Label	Present - Artwork	Artwork
Arabic Words of Care Labeling	Present - Artwork	
Size	Present - Artwork	
Country of Origin	Present - Artwork	

SASO STANDARDS		المتطلبات / المعايير
MANUFACTURER / EXPORTER	SWAYAM NERVA www.swayamnerva.com Tel. # 0091 9712366011	المصنع / المصدّر
BUYER	SASO	المشتري
PRODUCT NAME	OXFORD	اسم المنتج
COMPOSITION / CONTENT	ABT. 60% COTTON 40% POLYESTER	المصنوع / نوع القماش
DESIGN / COLOR NO.		التصميم / اللون
WEIGHT (GSM)	135GSM / 3.55 (GSM)	الوزن (GSM)
WIDTH	148 CM / 58 INCHES	العرض
LENGTH	ABT. 25 YARDS / 22.86 METRE	الطول
PURPOSE OF USE	UNIFORMS DRESS / SHIRTING	الغرض من الاستخدام
COUNTRY OF ORIGIN	INDIA	بلد المنشأ
DATE OF MANUFACTURE	SEPTEMBER 2018	تاريخ التصنيع
WASHING AND IRONING CARE INSTRUCTIONS		
تعليمات غسيل الملابس		
WASH BELOW 40 DEGREE CELSIUS	DO NOT BLEACH	TUMBLE DRY LOW
IRON AT NORMAL TEMPERATURE	DO NOT DRY CLEAN	DO NOT WRING
DRY IN SHADE ONLY		
MADE IN INDIA		
المصنوع في الهند		

END OF THE TEST REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Addressee in respect of this report and only accepts liability to the Addressee insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute.